

INSPECTION CERTIFICATE

KOBELCO WELDING OF EUROPE B.V.

FLUX CORED WIRE

PURCHASER _____

CERTIFICATE NO: KC24-248

DATE OF ISSUE: 17/07/2024

TRADE DESIGNATION	DIAMETER (mm)	MFG.NO.	APPLICABLE SPECIFICATION AND CLASSIFICATION
DW-316LP	1.2	N41070	AWS A5.22 E316LT1-1/4 EN ISO 17633-A T 19 12 3 L P C1/M21 1

1. CHEMICAL COMPOSITIONS OF ALL WELD METAL(wt%) (ACCORDING TO EN 10204 TYPE 3.1)

ELEMENT	C	Si	Mn	P	S	Cu	Ni	Cr	Mo	N	Nb	
WELD METAL	0.029	0.67	1.53	0.023	0.003	0.06	12.35	18.30	2.81	0.028	0.01	

ELEMENT	V		FS	FN		FNW						
WELD METAL	0.06		6.0	10.0		7.0						

FS:FERRITE CONTENT%(SCHAEFFLER DIAGRAM)
FN:FERRITE NUMBER(DELONG DIAGRAM)
FNW:FERRITE NUMBER(1992 WRC DIAGRAM)

2. MECHANICAL PROPERTY OF ALL WELD METAL (ACCORDING TO EN ISO)

2.a TENSILE TEST (ACCORDING TO EN 10204 TYPE 3.1)

YIELD STRENGTH at 0.2% OFFSET (MPa)	TENSILE STRENGTH (MPa)	ELONGATION GL=5D(%)
413	577	36

2.b CHARPY IMPACT (ACCORDING TO EN 10204 TYPE 3.1)

TESTING TEMPERATURE (°C)	ABSORBED ENERGY(J)	
	EACH	AVERAGE


3. WELDING CONDITIONS FOR THE TESTING

TYPE OF CURRENT	DC+	SHIELDING GAS	80%Ar+20%CO2
WELDING CURRENT	190 (A)	ARC VOLTAGE	28.0 (V)

4. REMARKS

BISMUTH (Bi) CONTENT IN DEPOSITED METAL IS NO LESS THAN 0.002%.
According to GofQ DW-316LP R0

WE HEREBY CERTIFY THAT THE TEST RESULTS OF THE ABOVE
WELDING MATERIAL ARE CORRECT



KOBELCO WELDING OF EUROPE B.V.
QA Manager